

WEST Search History

DATE: Thursday, October 23, 2003

Set Name Query side by side

Hit Count Set Name result set

DB=USPT,JPAB,EPAB,DWPI; PLUR=YES; OP=ADJ

L19	L18 and (nanocomposite or silicate)	1	L19
L18	polymerizable emulsifying agent	30	L18
L17	(emulsifying agent or emulsifier) with ((trimethyl ammonium chloride or trimethyl ammonium methyl sulfate or propane sulfonic acid or AMPS or dialkylaminoethyl methacrylate))	25	L17
L16	(emulsifying agent or emulsifier) same ((trimethyl ammonium chloride or trimethyl ammonium methyl sulfate or propane sulfonic acid or AMPS or dialkylaminoethyl methacrylate))	50	L16
L15	emulsif\$3 same ((trimethyl ammonium chloride or trimethyl ammonium methyl sulfate or propane sulfonic acid or AMPS or dialkylaminoethyl methacrylate))	187	L15
L14	reactive emulsif\$3 same ((trimethyl ammonium chloride or trimethyl ammonium methyl sulfate or propane sulfonic acid or AMPS or dialkylaminoethyl methacrylate))	1	L14
L13	reactive emulsif\$3 same ((trimethyl ammonium chloride or trimethyl ammonium methyl sulfate or propane sulfonic acid or AMPS or dialkylaminoethyl methacrylate))	1	L13
L12	nanocomposite and ((trimethyl ammonium chloride or trimethyl ammonium methyl sulfate or propane sulfonic acid or AMPS or dialkylaminoethyl methacrylate))	35	L12
L11	nanocomposite and ((trimethyl ammonium chloride or trimethyl ammonium methyl sulfate or propane sulfonic acid or AMPS or dialkylaminoethyl methacrylate)with (emulsif\$7))	0	L11
L10	nanocomposite and emulsif\$7	41	L10
L9	AMPS with emulsif\$5	27	L9
L8	AMPS adj2 emulsif\$5	2	L8
L7	5840796.pn.	2	L7
L6	L5 and nanocomposite	2	L6
L5	L4 or l3 or l2	167	L5
L4	yang-xiaoping\$.in.	5	L4
L3	larson-brent\$.in.	56	L3
L2	parker-dane\$.in.	108	L2
L1	parker-dane.in.	0	L1

END OF SEARCH HISTORY